

Nd-doped Potassium Gadolinium Tungstate Single Crystals

Nd:KGW crystals are low lasing threshold, highly efficient laser material exceptionally suitable for laser ranging applications.

The efficiency of Nd:KGW lasers is 3–5 times higher than the one of Nd:YAG lasers. Nd:KGW laser medium is one of the best choices ensuring effective laser generation at low pump energies (0.5 – 1 J). These crystals supplied by EKSPILA feature high optical quality and great value of bulk strength for laser radiation.

MATERIAL PHYSICAL AND LASER PROPERTIES

Chemical formula	$\text{KGd}(\text{WO}_4)_2\text{Nd}$
Lattice constants	$a = 8.095 \text{ \AA}$, $b = 10 \text{ \AA}$, $c = 7.588 \text{ \AA}$
Optical orientation	$n_g = b$, $n_p c = 20 \text{ deg}$
Angle between optical axis	86.5 angular grad
Density	7.27 g/cm ³
Mohs hardness	5
Thermal conductivity	2.8 W/(m×grad) [100] 2.2 W/(m×grad) [010] 3.5 W/(m×grad) [001]
Thermal expansion	$4 \times 10^{-6} \text{ grad}^{-1}$ [100] $3.6 \times 10^{-6} \text{ grad}^{-1}$ [010] $8.5 \times 10^{-6} \text{ grad}^{-1}$ [001]
Phase transition	1005 °C
Melting point	1075 °C
Transmission range	0.35-5.5 μm
Refractive index	$n_g = 2.033 @ 1.067 \text{ μm}$ $n_p = 1.937 @ 1.067 \text{ μm}$ $n_m = 1.986 @ 1.067 \text{ μm}$
Transition	$^4\text{F}_{3/2} \rightarrow ^4\text{I}_{11/2}$
Laser wavelength	1.0672 μm
Fluorescence lifetime	120 ms
Fluorescent width	24 cm ⁻¹
Emission cross-section	$4.3 \times 10^{-19} \text{ cm}^{-2}$
Emission temperature drift	$8.5 \times 10^{-4} \text{ nm, K}^{-1}$

Existing technology allows to obtain single crystals of mass up to 3 kg. This ensures reliable and high yield fabrication of round elements of diameter up to 12 mm and length up to 120 mm.

STANDARD PRODUCT SPECIFICATIONS

Orientation	[010] ±30 min
Dopant concentration	2-10 at %
Diameter tolerance	+0.0/-0.1 mm
Length tolerance	+1.0/-0.0 mm
Chamfer	45(±10) deg × 0.2(±0.1) mm
Flatness	λ/10 @ 633 nm
Parallelism	better than 30 arcsec
Perpendicularity	better than 15 arcmin
Surface finishing	10/5 scratch/dig
Absorption losses	< 0.005 cm ⁻¹

Please contact EKSPILA for further information or detailed quotation.



EKSPILA
 distributor in
United Kingdom

Ingcrys Laser Systems Ltd
 14 Parris Road, Stokenchurch,
 High Wycombe, Bucks. UK
 Tel.: + 44 (0) 1494 482541 | Fax: + 44 (0) 1494 482873
 E-mail: sales@ingcrys.com | www.ingcrys.com